

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶: A61L 15/00	A2	(11) International Publication Number: WO 99/64078 (43) International Publication Date: 16 December 1999 (16.12.99)
(21) International Application Number: PCT/US99/13073 (22) International Filing Date: 9 June 1999 (09.06.99) (30) Priority Data: 98110597.6 9 June 1998 (09.06.98) EP (71) Applicant (for all designated States except US): THE PROCTER & GAMBLE COMPANY [US/US]; One Procter & Gamble Plaza, Cincinnati, OH 45202 (US). (72) Inventors; and (75) Inventors/Applicants (for US only): CORZANI, Italo [IT/IT]; Via Fontevecchia, 40, I-66100 Chieti (IT). PALUMBO, Gianfranco [IT/DE]; Georgenfeld 7, D-61348 Bad Homburg (DE). (74) Agents: REED, T., David et al.; The Procter & Gamble Company, 5299 Spring Grove Avenue, Cincinnati, OH 45217-1087 (US).		(81) Designated States: AE, AL, AM, AT, AT (Utility model), AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, CZ (Utility model), DE, DE (Utility model), DK, DK (Utility model), EE, EE (Utility model), ES, FI, FI (Utility model), GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SK (Utility model), SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>Without international search report and to be republished upon receipt of that report.</i>

(54) Title: SHAPE-FORMED, THREE DIMENSIONAL, MOISTURE VAPOUR PERMEABLE, LIQUID IMPERMEABLE ARTICLES COMPRISING MOISTURE VAPOUR PERMEABLE, LIQUID IMPERMEABLE STRUCTURES COMPRISING LOW VISCOSITY THERMOPLASTIC COMPOSITIONS**(57) Abstract**

The present invention relates to shape-formed, three dimensional, moisture vapour permeable, liquid impermeable articles comprising moisture vapour permeable, liquid impermeable structures comprising a thermoplastic composition having a higher processability. The thermoplastic compositions comprise preferred thermoplastic polymers and suitable plasticisers to adjust the viscosity of the composition at the process conditions. The shape-formed three dimensional articles of the present invention can find a variety of applications wherein moisture vapour permeability combined with liquid imperviousness are desirable.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

**SHAPE-FORMED, THREE DIMENSIONAL, MOISTURE VAPOUR
PERMEABLE, LIQUID IMPERMEABLE ARTICLES COMPRISING MOISTURE
VAPOUR PERMEABLE, LIQUID IMPERMEABLE STRUCTURES
COMPRISING LOW VISCOSITY THERMOPLASTIC COMPOSITIONS**

Field of the Invention

The present invention relates to shape-formed three dimensional articles which are moisture vapour permeable and liquid impermeable and comprise moisture vapour permeable, liquid impermeable formed structures comprising thermoplastic compositions having a higher processability. The shape-formed three dimensional articles of the present invention can find a variety of applications wherein moisture vapour permeability combined with liquid imperviousness are desirable

Background of the Invention

Articles comprising structures which provide a liquid barrier in addition to providing moisture vapour permeability are known in the art. Particularly preferred for this type of moisture vapour permeable, liquid impermeable articles are hydrophilic thermoplastic compositions forming a continuous structure, e.g. a continuous film that does not allow the flow of moisture vapour through open pores or apertures in the material, but does transfer substantial amounts of moisture vapour through the film by absorbing water on one side of the film where the moisture vapour concentration is higher, and desorbing or evaporating it on the opposite side of the film where the moisture vapour concentration is lower.

For example WO 95/16746 discloses films prepared from mixtures of a) block copolyether ester, block copolyether amides (e.g. Pebax™) and or polyurethane and b) thermoplastic polymer which is incompatible with (a), and c) a compatibiliser. The films are liquid impermeable and have moisture vapour permeability of about 700 g/m²·day. Also, US 5,447,783 discloses a vapour permeable water resistant multi component film structure having at least three layers. The outer layers are hydrophobic copolyetherester elastomers having a thickness of 1.3-7.6 micrometers and a WVTR of 400-2500 g/m²·24h and the inner layer is a hydrophilic copolyetherester elastomer having a thickness of 7.6 - 152 micrometers and a WVTR of at least 3500 g/m²·24h.

US 5,445,875 discloses a waterproof, bloodproof and virusproof breathable laminate. The laminate comprises a woven/nonwoven fabric and an extruded film such as Hytrel™ having a thickness of about 1mil (25.4 micrometers).

Other composite laminates are described for example in US 5,599,610 which discloses tri-laminated fabric for surgical gowns comprising outer layers of woven fabric and an inner layer of a microporous polyurethane membrane. The microporous film has a thickness of 12-55 micrometers and a MVTR of 1100 g/m²·24h upright and 5500 g/m²·24h inverted (ASTM E96-B). Polyether-polyurethane adhesive is used to join the layers.

Similarly, US 5,532,053 discloses a high moisture transmission medical film which can be laminated onto a nonwoven material. The laminate film comprises a first layer of polyetherester copolymer and second and third layers selected from a specified group of polymers. The film has a MVTR of greater than 750 g/m²·24h (ASTM F1249) and a thickness of less than 1 mil (25.4 micrometer) preferably 0.6 mil to 0.75 mil (15 -19 micrometers).

US 4,938,752 discloses absorbent articles comprising films of copolyether esters which have reduced water permeability, a water vapour permeability of 500 g/m²·24h (as measured in a specified described test) and a thickness of 5-35 micrometers. There is no disclosure of a supportive substrate.

US 4,493,870 discloses a flexible layered waterproof product comprising a textile material covered with a film of a copolyetherester having an MVTR of at least 1000 g/m²·24h (ASTM E96- 66) having a thickness of 5 to 35 micrometers.

5 GB 2024100 discloses a flexible layered water resistant article comprising a microporous hydrophobic outer layer which is moisture vapour permeable but resist liquids and a hydrophilic inner layer of polyetherpolyurethane having a MVTR of above 1000 g/m²·24h.

10 Compositions known for providing hydrophilic continuous moisture vapour permeable, liquid impermeable structures, e.g. in form of films or layers, include thermoplastic polymers such as polyurethanes, poly-ether-amides block copolymers, polyethylene-acrylic acid copolymers, polyethylene oxide and its
15 copolymers, poly lactide and copolymers, polyamides, polyester block copolymers, sulfonated polyesters, poly-ether-ester block copolymers, poly-ether-ester-amide block copolymers, polyacrylates, polyacrylic acids and derivatives, ionomers, polyethylene-vinyl acetate with a vinyl acetate content of more than 28% by weight, polyvinyl alcohol and its copolymers, polyvinyl ethers
20 and their copolymers, poly-2-ethyl-oxazoline and derivatives, polyvinyl pyrrolidone and its copolymers, thermoplastic cellulose derivatives, or mixtures thereof. Such compositions can be used for making formed structures, e.g. layers and films, featuring high values of moisture vapour permeability while being liquid impermeable, which therefore are particularly preferred for incorporation in shape-formed three dimensional moisture vapour permeable, liquid impermeable
25 articles wherein moisture vapour permeability together with liquid imperviousness is provided by such formed structures.

However, a problem associated with shape-formed three dimensional, moisture vapour permeable liquid impermeable articles comprising formed
30 structures, e.g. films or layers, made from the above mentioned thermoplastic compositions is that such compositions are typically highly viscous in the plastic state at the process conditions, and require complex processing techniques and equipment. They are typically processable by means of extrusion techniques. Extrusion processes for making formed structures, e.g. films or layers, from
35 thermoplastic polymers are well known, but have the disadvantage of being rather complex; they in fact require expensive equipment, typically comprising a

high power screw extruder to force the material in the plastic state through e.g. a slit die to form the film or layer. Extrusion process conditions also typically involve rather high temperatures and pressures. Moreover an extrusion apparatus for the formation of a film or layer cannot be easily incorporated into a production line, e.g. of a shape-formed three dimensional moisture vapour permeable liquid impermeable article comprising a moisture vapour permeable liquid impermeable structure comprising such thermoplastic compositions. Extrusion processes moreover are not suitable for the production of films having a particularly low thickness, e.g. in the range of 5-10 μm . Other processes that could be used in the manufacturing of shape-formed three dimensional moisture vapour permeable liquid impermeable articles are either not suitable, or at least more problematic when applied to the above mentioned preferred thermoplastic compositions.

Furthermore, in case of shape-formed three dimensional moisture vapour permeable articles comprising laminated composite moisture vapour permeable structures, in which i.e. a layer of the preferred moisture vapour permeable, liquid impermeable composition is laminated to a substrate, e.g. a fibrous layer, the addition of an adhesive in order to ensure permanent fixation of the film onto the substrate is often required. However, this in turn detrimentally affects the overall moisture vapour permeability of the resulting composite, and adds complexity to the production process.

Hence, there is a need to provide shape-formed three dimensional articles which are moisture vapour permeable and liquid impermeable and comprise moisture vapour permeable, liquid impermeable formed structures comprising thermoplastic compositions, said structures providing the articles with the preferred characteristics of moisture vapour permeability and liquid imperviousness, wherein said compositions have a higher processability so as to provide said moisture vapour permeable structures, e.g. in the form of a preferably thin film.

Summary of the Invention

The present invention relates to a shape-formed, three dimensional, moisture vapour permeable, liquid impermeable article comprising a moisture

vapour permeable, liquid impermeable structure comprising a thermoplastic composition comprising:

5 a thermoplastic polymer or mixture of polymers having a viscosity higher than 5000 poise at a temperature of 20°C above the DSC melting point of the polymer or mixture of polymers, evaluated as described in the text, and at a frequency of 1 rad/sec, the thermoplastic polymers being selected from the group consisting of polyurethanes, poly-ether-amides block copolymers, polyethylene-acrylic acid copolymers, polyethylene oxide and its copolymers, poly lactide and copolymers, 10 polyamides, polyester block copolymers, sulfonated polyesters, poly-ether-ester block copolymers, poly-ether-ester-amide block copolymers, polyacrylates, polyacrylic acids and derivatives, ionomers, polyethylene-vinyl acetate with a vinyl acetate content of more than 28% by weight, polyvinyl alcohol and its copolymers, polyvinyl ethers and their copolymers, poly-2-ethyl-oxazoline and 15 derivatives, polyvinyl pyrrolidone and its copolymers, thermoplastic cellulose derivatives, or mixtures thereof,

a suitable compatible plasticiser or blend of plasticisers for adjusting said viscosity,

20 wherein said thermoplastic composition has a viscosity of from 50 poise to 4000 poise at a frequency of 1 rad/s at a temperature of 210°C or less and a viscosity of less than 2000 poise at a frequency of 1000 rad/s at a temperature of 210°C or less.

25

Detailed Description of the Invention

According to the present invention, shape-formed, three dimensional moisture vapour permeable liquid impermeable articles are provided which 30 comprise moisture vapour permeable, liquid impermeable structures comprising highly processable low viscosity thermoplastic compositions.

The highly processable, low viscosity thermoplastic compositions can comprise the majority or sole material of the shape-formed three dimensional article of the present invention. In the latter case, the structure is entirely made of 35 the thermoplastic composition, and in turn the article is entirely constituted by the

structure. Alternatively, the thermoplastic compositions can be utilised in combination with one or more other materials to create a composite structure comprised in the article, or also the thermoplastic composition can constitute entirely a structure, which is then combined with other elements in the article of the present invention. In many cases, it may be preferred that the shape-formed article be comprised substantially or wholly by the thermoplastic composition, which can provide structure without use of additional materials.

Said thermoplastic compositions are useful in the incorporation into the articles of the present invention which are shape-formed, three dimensional as delivered to the consumer. Said articles therefore possess at least one region that displays some three dimensional form or shape in contrast to a two dimensional or planar form. Such three dimensional form or shape may involve simple or complex surface geometries. Examples to illustrate the range include simpler constructions such as two planes joined at a line defining a right (90 degree) angle or a simple sphere to more complex constructions such as two wave form surfaces intersecting in a non-linear fashion.

Said shape formed articles may be shaped in a closed form, such as a spherical ball or a cube, or shaped with one or more openings, such as a hand covering or glove.

In response to an introduced force or pressure, the article may display deformation, that is change or alter its shape. Though not limited to the following definitions, such deformation can be thought of as a general expansion or contraction of the overall article, in one way measured by a change in enclosed volume within the general boundaries of the surfaces of the article or alternatively measured by a change in the volume of the circumscribed space as defined by the outermost surfaces of the article.

Such introduced forces or pressures include, but are not restricted to, externally or internally applied pressure increases or decreases (vacuum); mechanical compression forces; and, tensile forces being applied within the articles walls themselves (i.e. stretching a portion of the article wall).

Once the applied force or pressure is removed, the post-deformation response of the article can range from full shape recovery to an irreversible shape change.

5 Such articles can be re-used many times or be so constructed that the intended article life is but one use before disposal or refurbishment.

10 The shape-formed, three dimensional articles of the present invention can be employed in a variety of usage areas particularly when water vapour permeation is needed but liquid barrier protection is still desired. There are other usage situations where the articles of the present invention employing the thermoplastic composition can provide other barrier functions such as pathogen barrier, barrier to undesirable or hazardous chemicals such as those causing a deleterious effect on human skin, or provide selective barrier for other specific
15 elements to be blocked such as specific chemicals, gasses or biological entities.

20 The following paragraphs provide example categories of use where the articles of this invention can provide useful advantage. The listing of categories is intended for illustration purposes and is not all-inclusive and therefore is not limiting.

25 As an illustrative example, one category of shape-formed, three dimensional articles beneficial to humans and other living creatures are bodily protective, hygienic or comfort articles such as, but not limited to: hand coverings such as gloves, finger cots, mitts, mittens; foot or leg coverings such as socks, hose, pantyhose, shoes, slippers; head coverings such as hats, caps; prophylactic articles such as condoms, semen shields internally placed inside the vaginal cavity; face coverings such as face masks, nose covers, ear covers or mitts; body support items such as male organ "athletic" supporters, brassieres;
30 formed clothing for use as underwear, protective sleeves, or as a part of or wholly incorporated into protective pads. Other example articles and applications include but are not limited to: flexible or drapable clothing articles for humans or other living creatures such as the non-limiting examples of shirts, pants, undergarments, bibs, smocks, coats, scarves, body wraps, stockings, leggings, skirts, dresses, etc.; other flexible or drapable clothing for various tasks and
35 occupations including medical professions, agricultural jobs, mechanical

assembly and repair, emergency public services, the military, athletic endeavours, cleaning positions, etc.

5 A preferred category of shape-formed, three dimensional articles according to the present invention comprises said hand covering articles, and more specifically gloves, also including gloves made of two flat material portions, at least one material portion comprising the structure of this invention, which are joined around a common perimeter typically defining the shape of a hand, and which later take a fuller, higher volume three dimensional shape when a hand is
10 inserted during later use through an opening comprised in said perimeter.

Another example category of use involves packaging such as with food products such as fresh produce and baked goods (bread, rolls, cakes) as non-limiting examples.

15

A further example category of use involves agriculture and horticulture such as, as non-limiting examples, an individual article (container, three dimensional "bag") which is placed to partially or totally enclose an individual or specific group of plants.

20

An even further example category of use involves protective furniture coverings such as protective covers for upholstered chairs and sofas, etc.

25 Said shape-formed, three dimensional articles of the present invention can be formed or shaped by a variety of known thermoplastic forming methods. A class of such methods is generally described as "moulding" where the material is often shaped via use of male or female moulds or combinations of moulds. Depending on the technique, certain processing temperature and pressure (or vacuum) conditions may be preferred for production of a given article. Such
30 known moulding methods include, but are not limited to: dip moulding, blow moulding, injection moulding, compression moulding, thermoforming, vacuum thermoforming, extrusion moulding, rotational moulding, slush moulding, etc.

35 Afterward, the article and mould(s) are separated. Often there may be an intervening process step between contact of the thermoplastic composition and separation of the shape formed article and mould. The nature of the intervening

step or steps will vary depending on moulding technique, environmental condition, material format, etc. For example, a dip moulded article may need to be processed to remove: (i) solvent from the article if a solvent-based format of the raw material form of the thermoplastic composition is chosen; (ii) water from the article if a emulsion-based format of the raw material form of the thermoplastic composition is chosen; or, (iii) heat if a hot melt format of the raw material form of the thermoplastic composition is chosen. Of course this further removing process step can be applied to any of the known forming methods described herein with reference to the thermoplastic compositions of this invention (e.g. moulding, or casting, or coating).

Other known methods for producing the shape-formed, three dimensional articles of the present invention, namely for processing the thermoplastic compositions comprised herein, also include: film and sheet casting; blown film techniques; an additional tentering process step; an additional calendering step; an additional quenching step; an additional heat treatment step; etc. The nature of the specific production conditions or type or order of process steps will vary depending on the chosen making technique, environmental condition, material format, etc. For example, a process step may need to be included to remove: (i) solvent; (ii) water; or, (iii) heat as explained above with reference to the dip moulding process.

Regarding casting, the thermoplastic composition may be cast onto a moving cylinder, belt, web, release substrate (including release papers and films), etc. into e.g. a film or sheet. The film or sheet can be later separated from the casting surface.

A film or sheet can be produced with two or more layers where at least one of the layers comprises the thermoplastic composition of this invention. This can be accomplished by a variety of known means, including but limited to: co-extrusion, extrusion coating, etc.

The resulting materials are then typically post formed into a shaped form such as by thermoforming, vacuum thermoforming, and other known processing methods for shaping or forming thermoplastic films and sheets.

While it may be at times preferable that the entire shape-formed portion of the three dimensional article of the present invention be comprised solely of the thermoplastic composition, the article can be a composite with one or more other materials. The composite, for example, can involve two or more components of the specific thermoplastic composition within the present invention or different specific thermoplastic compositions of the present invention.

Alternatively, the composite can involve at least one component of the thermoplastic composition in combination with one or more other materials. Such materials include, but are not limited to: fibres, fibrous batts, non-wovens, wovens, papers, metal foils, micro-porous or porous membranes, films such as polymeric films, inorganic structures such as compressed gypsum sheets, perforated or apertured films and papers, macroscopically expanded films, cloth, substantially rigid fibre-based materials such as lumber, etc.

Said other components may be non-absorbent, absorbent, liquid-containing, etc.

Preferably the composite structures described above have a moisture vapour transfer rate of at least $100 \text{ g/m}^2\cdot 24\text{h}$, more preferably at least $300 \text{ g/m}^2\cdot 24\text{h}$, and most preferably at least $500 \text{ g/m}^2\cdot 24\text{h}$.

Said composite can be assembled later after at least two separate components of the shape-formed, three dimensional article of the present invention have been partially or wholly processed, with at least one of said components being of the thermoplastic composition. Such components can be brought together in a variety of known approaches including but not limited to: sealing such as heat sealing, ultrasonic or pressure bonding or welding, RF sealing, laser sealing, etc.; crimping; adhering via use of adhesives, glues, reactive bonding materials, wetting with water or other liquids, etc.; mechanical fastening or connection via hook and loop systems, nails, staples, hardware fasteners such as hook & grommet or bolt and nut; etc.; use of attractive forces including electromagnetic forces (e.g. magnetism) and electrical charge (e.g. static electricity).

Alternatively or in addition, other material(s) can be introduced during the thermoplastic composition forming process, e.g. moulding, to allow concurrent mating with the other material(s) into a composite article during the shape forming step. A second material can be e.g. introduced which comprises numerous separate individual pieces, for example fibres. As a non-limiting example, a portion of the surface of the article can be contacted during the moulding process with a fibrous material to create a flocked surface without need for conventional adhesives normally used for flocking. An example product would be a glove.

Another useful technique is the process of spray coating. The thermoplastic composition of this invention lends itself to a heated spraying technique whereas upon heating the viscosity is sufficiently lowered to allow spray coating or sputtering. Such thermoplastic composition spray coating can occur with the aid of a mould, either male or female, to build surfaces or walls of the article. Afterward, the article and mould (or mould parts) are separated from each other. Alternately, the spray coating method can employ different starting raw material formats of the polymer composition such as a solvent-based approach or an emulsion.

For a composite article employing the spray coating approach, the other material may provide sufficient three dimensional structure by itself such that the other material acts as the mould, after which it is sufficiently coated the composite article is complete, avoiding the before-mentioned separation of article from mould. Said combined article component and mould can also comprise a flattened glove liner that may lie somewhat flat during polymer introduction, for example via spray coating, and then later takes a fuller, higher-volume shape when a hand is inserted during later use.

The thickness of the shape-formed article of this present invention can be constant or vary within the structure. Though not limited to any specific thickness range, depending upon application there may be preferred ranges. For example, the preferred range for a worn personal hygiene article may desirously range from as thick as 400 microns down to less than 0.5 microns and more preferably, in certain cases, substantially less than 0.5 microns. In contrast, a construction

or even packaging application may, for certain reasons, dictate a preferred range from 200 to 2000 microns or even thicker.

Said article can possess areas where no polymer is present ranging from
5 voids so small to be considered micro-porous to larger scale, macroscopic-sized voids. A portion or all of the article's surface can be apertured whereas the apertures can be a rather simple geometry like a hole or slit; or, the discrete apertures can extend beyond the horizontal plane of the surface. As an example, the protuberances can have an orifice located at its terminating end.
10 As further example, said protuberances are of a funnel shape, similar to those described in US 3929135. The apertures located within the plane and the orifices located at the terminating end of protuberance themselves maybe circular or non circular provided the cross sectional dimension or area of the orifice at the termination of the protuberance is smaller than the cross sectional dimension or
15 area of the aperture located within the garment facing surface of the layer. Preferably said apertured performed films are uni directional such that they have at least substantially, if not complete one directional fluid transport.

Preferred thermoplastic polymers comprised in the thermoplastic
20 composition of this invention are polyurethanes, poly-ether-amides block copolymers, polyethylene-acrylic acid copolymers, polyethylene oxide and its copolymers, poly lactide and copolymers, polyamides, polyester block copolymers, sulfonated polyesters, poly-ether-ester block copolymers, poly-ether-ester-amide block copolymers, polyacrylates, polyacrylic acids and
25 derivatives, ionomers, polyethylene-vinyl acetate with a vinyl acetate content of more than 28% by weight, polyvinyl alcohol and its copolymers, polyvinyl ethers and their copolymers, poly-2-ethyl-oxazoline and derivatives, polyvinyl pyrrolidone and its copolymers, thermoplastic cellulose derivatives, and mixtures thereof. Among the above mentioned thermoplastic polymers particularly
30 preferred are thermoplastic poly-ether-amide block copolymers (e.g. Pebax™), thermoplastic poly-ether-ester-amide block copolymers, thermoplastic polyester block copolymers (e.g. Hytrel™), thermoplastic polyurethanes (e.g. Estane™), or mixtures thereof. Such thermoplastic polymers or mixture of polymers are typically highly viscous in the melted state at the process conditions that are
35 typical of the known processes of film or layer formation, e.g. an extrusion process involving a high power screw extruder. Specifically the thermoplastic

polymer or mixture of polymers typically have a viscosity higher than 5000 poise at a temperature of 20°C above the DSC (Differential Scanning Calorimetry) melting point, which is the temperature identified as that corresponding to the DSC peak, or corresponding to the highest DSC peak in case of a mixture of polymers showing more than one peak, and at a frequency of 1 rad/sec.

The viscosity of the thermoplastic compositions comprised in the shape-formed, three dimensional articles of the present invention is adjusted by providing the thermoplastic composition comprising the thermoplastic polymer or mixture of polymers with a suitable plasticiser, or blend of plasticisers, that is compatible with the thermoplastic polymers and that lowers the viscosity of the thermoplastic composition in the melted state.

According to the present invention the thermoplastic compositions have the following complex viscosities (η^*):

50 poise $< \eta^* < 4000$ poise, preferably 100 poise $< \eta^* < 2000$ poise, more preferably 100 poise $< \eta^* < 1000$ poise, at a frequency of 1 rad/s at a temperature of 210°C or less and $\eta^* < 2000$ pose, preferably $\eta^* < 1000$ poise, more preferably $\eta^* < 500$ poise at a frequency of 1000 rad/s at a process temperature (T) of 210°C or less, wherein η^* represents the complex viscosity of the thermoplastic polymeric composition. Preferably the temperature T is 200°C or less and more preferably 180°C or less and most preferably from 200°C to 50°C.

25

It has been surprisingly found that thermoplastic compositions having the complex viscosity described are more easily processable in order to provide the moisture vapour permeable, liquid impermeable structures comprised in the articles of the present invention. For example, said thermoplastic compositions allow for a film or layer to be e.g. coated onto a substrate using typical coating conditions and apparatuses known in the art for the coating of low viscosity hot melt compositions in a layer having a required thickness onto a substrate, while keeping the advantageous characteristics of the preferred thermoplastic polymers in providing hydrophilic continuous moisture vapour permeable, liquid impermeable layers or films. Other known methods for making three dimensional articles such as moulding, casting, and others as described above, also take

advantage from the lower viscosity of the thermoplastic compositions comprised herein.

It has also been found that thermoplastic compositions having such
5 viscosities can provide very thin films or layers.

Suitable plasticisers for use in the thermoplastic compositions comprised in the three dimensional articles according to the present invention include esters of
citric acid, tartaric acid, maleic acid, sorbic acid, fumaric acid, lactic acid, glyceric
10 acid, malic acid; glycerol and its esters, adipates, sebacates, sorbitol, epoxidized
vegetal oils, polymerised vegetal oils, polyols, phthalates, liquid polyesters,
glycolates, p-toluene sulfonamide and derivatives, glycols and polyglycols,
sorbitan esters, phosphates, monocarboxylic fatty acids (C_8 - C_{22}) and their
derivatives, and mixtures thereof.

15

Preferably the thermoplastic composition comprised in the shape-formed
three dimensional articles of the present invention comprises from 10% to 80%,
more preferably from 25% to 70% by weight of the thermoplastic composition, of
the thermoplastic polymer or mixture of polymers, and from 20% to 90%,
20 preferably from 30% to 75% by weight of the thermoplastic composition, of the
suitable plasticiser or blend of plasticisers.

The thermoplastic compositions comprised in the shape-formed three
dimensional articles of the present invention may in addition comprise additional
25 optional components to further improve the processability of the compositions
and also the mechanical characteristics as well as other characteristics as
tackiness, resistance to ageing by light and oxygen, visual appearance etc., of
the structures, e.g. films or layers, formed from such thermoplastic compositions.

Such optional components include tackifying resins or blends of tackifying
resins having a softening point of 125°C or less. Preferred resins, which may be
present by up to 50% by weight of the thermoplastic composition, may be
selected from rosins and rosin esters, hydrocarbon resins, aliphatic resins,
terpene and terpene-phenolic resins, aromatic resins, synthetic C_5 resins,
35 mixtures of synthetic C_5 - C_9 resins, and mixtures thereof. Other optional
components of said thermoplastic compositions include anti-oxidants, anti-

ultraviolets, pigments and mixtures thereof, which may be present within the composition at a level of up to 10% by weight of the composition.

5 A thermoplastic composition comprised in the moisture vapour permeable liquid impermeable structures in turn comprised in the shape-formed three dimensional moisture vapour permeable liquid impermeable articles according to the present invention can be manufactured with a process that will typically comprise the steps of providing the thermoplastic polymer or mixture of polymers and the suitable plasticiser or blend of plasticisers, heating the components and
10 compounding them, e.g. with a known suitable mixer to form the thermoplastic composition in the molten state having the desired complex viscosity η^* .

According to an aspect of the present invention a moisture vapour permeable, liquid impervious structure, e.g. in the form of a layer, can be formed
15 from the thermoplastic composition described above for example by coating said thermoplastic composition onto a substrate.

The moisture vapour permeable liquid impermeable structures, e.g. in form of films or layers, comprising said thermoplastic compositions preferably have a
20 moisture vapour transport rate of at least $100 \text{ g/m}^2 \cdot 24\text{h}$, preferably at least $300 \text{ g/m}^2 \cdot 24\text{h}$, most preferably at least $500 \text{ g/m}^2 \cdot 24\text{h}$, with a thickness of at least $0.5 \mu\text{m}$.

A process for making a moisture vapour permeable liquid impermeable
25 structure, e.g. in form of a layer or film, from a thermoplastic composition which is intended to be comprised in a shape-formed three dimensional moisture vapour permeable liquid impermeable article according to the present invention can for example comprise the steps of providing said composition, heating it to make it flowable, and coating said composition in the molten state onto a substrate in a
30 layer having the desired thickness. The structure can be included or formed into a shape-formed three dimensional moisture vapour permeable liquid impermeable article according to the present invention, e.g. hand covering articles such as finger cots, mitts, mittens, gloves, or other articles as described above, by means of one of the method known in the art. While said substrate can
35 be simply a formation substrate, onto which the thermoplastic composition is coated in order to form a film or layer of the desired thickness which is

subsequently separated from said substrate and used as such, in an embodiment of the present invention a moisture vapour permeable, water impervious composite structure can also be formed which comprises the thermoplastic composition and a substrate onto which said thermoplastic composition is coated, wherein the substrate is also preferably moisture vapour permeable.

Such embodiment of the present invention provides a moisture vapour permeable, liquid impervious composite structure, comprised in a shape-formed three dimensional moisture vapour permeable liquid impermeable article, wherein the contribution of the layer formed from the thermoplastic composition of the present invention to the performance of the composite material resides only in the provision of a liquid barrier and hence could be advantageously provided as thinly as possible. The remaining performance physical criterion being preferably provided by the provided substrate, that therefore preferably acts also as a support layer.

The substrate, or support layer may be any useful layer which is preferably also moisture vapour permeable, preferably having a moisture vapour permeability of at least $100 \text{ g/m}^2\cdot 24\text{h}$, more preferably at least $300 \text{ g/m}^2\cdot 24\text{h}$, and most preferably at least $500 \text{ g/m}^2\cdot 24\text{h}$.

Suitable substrates for use herein as support layers include two dimensional, planar micro and macro-porous films; macroscopically expanded films; formed apertured films; nonwoven and woven layers. According to the present invention the apertures in said layer may be of any configuration, but are preferably spherical or oblong and may also be of varying dimensions. The apertures preferably are evenly distributed across the entire surface of the layer, however layers having only certain regions of the surface having apertures are also envisioned.

Suitable two dimensional porous planar layers of the backsheet may be made of any material known in the art, but are preferably manufactured from commonly available polymeric materials. Suitable materials are for example Goretex™ or Sympatex™ type materials well known in the art for their application in so-called breathable clothing. Other suitable materials include

XMP-1001 of Minnesota Mining and Manufacturing Company, St. Paul, Minnesota, USA and Exxaire XBF-101W, supplied by the Exxon Chemical Company. As used herein the term two dimensional planar layer refers to layers having a depth of less than 1 mm, preferably less than 0.5 mm, wherein the apertures have an average uniform diameter along their length and which do not protrude out of the plane of the layer. The apertured materials for use as a backsheet in the present invention may be produced using any of the methods known in the art such as described in EPO 293 482 and the references therein. In addition the dimensions of the apertures produced by this method may be increased by applying a force across the plane of the backsheet layer (i.e. stretching the layer).

Suitable apertured formed films include films which have discrete apertures which extend beyond the horizontal plane of the garment facing surface of the layer towards the core thereby forming protuberances. The protuberances have an orifice located at its terminating end. Preferably said protuberances are of a funnel shape, similar to those described in the already mentioned US 3,929,135.

Suitable macroscopically expanded films for use herein include films as described in for example in US 4,637,819 and US 4,591,523.

Preferred support layers for use herein include woven and nonwoven layers, most preferably hydrophobic fibrous layers such as hydrophobic nonwoven.

The composite moisture vapour permeable structures of this embodiment of the present invention are particularly advantageous as they allow the possibility of providing a composite wherein the thermoplastic composition may be coated onto the support substrate as a layer with the desired thickness. Typical coating conditions and apparatuses known in the art for the direct coating of low viscosities hot melts can be readily utilised in order to provide the thermoplastic composition at the desired thickness.

A possible method for forming a composite laminate by coating the thermoplastic composition onto a substrate acting as a support layer is described in PCT application WO 96/25902.

At least at the coating temperature, the thermoplastic composition in form of a layer preferably exhibits adhesive properties on the supportive substrate in order to form the moisture vapour permeable composite structure such that no additional adhesive is required to achieve a permanent attachment between the thermoplastic composition and the substrate. In some applications it may be also desirable that the thermoplastic composition remains tacky at any temperature i.e. it is formulated so to have the typical characteristics of a pressure sensitive adhesive.

10

The shape-formed three dimensional moisture vapour permeable liquid impermeable articles of the present invention comprising the moisture vapour permeable liquid impermeable structures in turn comprising the low viscosity thermoplastic compositions described above find utility in a number of applications wherein liquid imperviousness and moisture vapour permeability are desirable. In particular the present invention can be effectively utilised within shape-formed three dimensional moisture vapour permeable liquid impermeable articles such as e.g. hand covering articles comprising finger cots, mitts, mittens and preferably gloves, and also other articles as described above. Preferably the moisture vapour permeable, liquid impervious structures, e.g. layers or composites, formed from the thermoplastic compositions described so far and comprised in the shape-formed three dimensional moisture vapour permeable liquid impermeable articles of the present invention have a moisture vapour transfer rate of at least $100 \text{ g/m}^2 \cdot 24\text{h}$, more preferably at least $300 \text{ g/m}^2 \cdot 24\text{h}$, and most preferably at least $500 \text{ g/m}^2 \cdot 24\text{h}$.

15

20

25

Example:

A polyether-amide block copolymer available from Elf Atochem (France) commercialised under the trade name Pebax MV 1074 was compounded with Triethyl Citrate available from Aldrich Co. and Irganox 1010 (anti oxidant agent) available from Ciba-Geigy.

30

The polymer has a DSC peak melting point of 158°C and at 178°C and at the frequency of 1 rad/s shows a complex viscosity of 6410 Poise .

35

The final formulation in percent by weight had the following composition:

30%	Pebax MV 1074
69%	Triethyl Citrate
1%	Irganox 1010

5 The blend was melt extruded at 160°C to obtain a film having a thickness equal to 5µm. At the extruding temperature it was found to have complex viscosities of 517 poise and 172 Poise respectively at 1 and 1000 rad/s shear rate. The film was then laminated directly onto a substrate constituted by a carded hydrophobic 100% polypropylene nonwoven 34 g/m² (support layer) 10 commercialised under the trade name Sawabond 4326, available from Sandler (Germany). The composite structure had a moisture vapour transfer rate of 2530 g/m².24hrs, and could be formed or comprised into a shape-formed three dimensional moisture vapour permeable liquid impermeable article according to the present invention with one of the methods known in the art.

15 According to the present invention the complex viscosity is measured using a Rheometer RDA-II available from Rheometrics Co. Water vapour permeability is measured at 23°C according to the ASTM E-96 "Upright Cup" method.

CLAIMS

5

1. A shape-formed, three dimensional, moisture vapour permeable, liquid impermeable article comprising a moisture vapour permeable, liquid impermeable structure, said structure comprising a thermoplastic composition, said composition comprising:

10

a thermoplastic polymer or mixture of polymers having a viscosity higher than 5000 poise at a temperature of 20°C above the DSC melting point of said polymer or mixture of polymers and at a frequency of 1 rad/sec, said thermoplastic polymers selected from the group consisting of

15 polyurethanes, poly-ether-amides block copolymers, polyethylene-acrylic acid copolymers, polyethylene oxide and its copolymers, poly lactide and copolymers, polyamides, polyester block copolymers, sulfonated polyesters, poly-ether-ester block copolymers, poly-ether-ester-amide block

20 copolymers, polyacrylates, polyacrylic acids and derivatives, ionomers, polyethylene-vinyl acetate with a vinyl acetate content of more than 28% by weight, polyvinyl alcohol and its copolymers, polyvinyl ethers and their copolymers, poly-2-ethyl-oxazoline and derivatives, polyvinyl pyrrolidone and its copolymers, thermoplastic cellulose derivatives, or mixtures thereof,

25

a suitable compatible plasticiser or blend of plasticisers for adjusting said viscosity,

30

wherein said thermoplastic composition has a viscosity of from 50 poise to 4000 poise at a frequency of 1 rad/s at a temperature of 210°C or less and a viscosity of less than 2000 poise at a frequency of 1000 rad/s at a temperature of 210°C or less.

35

2. A shape-formed, three dimensional, moisture vapour permeable, liquid impermeable article according to claim 1, wherein said article comprises said structure and wherein said structure is made of said thermoplastic

composition, said structure having a water vapour transmission rate (WVTR) of at least $300 \text{ g/m}^2 \cdot 24\text{h}$ with a thickness of said structure of at least $0.5 \text{ }\mu\text{m}$.

- 5 3. A shape-formed, three dimensional, moisture vapour permeable, liquid impermeable article according to claim 2, wherein said article is made of said structure.
- 10 4. A shape-formed, three dimensional, moisture vapour permeable, liquid impermeable article according to any preceding claim, wherein said article is a hand covering article.
- 5 5. A shape-formed three dimensional moisture vapour permeable liquid impermeable article according to claim 4, wherein said article is a glove.
- 15 6. A process for making a shape-formed, three dimensional, moisture vapour permeable, liquid impermeable article according to claim 1, comprising the steps of:
 - 20 • providing said thermoplastic composition,
 - forming said thermoplastic composition into said structure by means of a moulding, or casting, or coating method,
 - 25 • forming said structure into said article.
- 30 7. A process according to claim 6, wherein said thermoplastic composition is provided in a solvent-based format, or in a hot-melt format, or in an emulsion-based format.
- 35 8. A process according to claim 6 or 7, wherein said process comprises the further step of:
 - concurrently mating a second material with said thermoplastic composition when forming said thermoplastic composition into said structure, wherein said structure is a composite structure.

9. A process according to claim 8, wherein said second material comprises numerous separate individual pieces.
- 5 10. A process according to claim 9, wherein said second material comprises flocking fibres in order to provide said composite structure with a flocking surface.

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
16 December 1999 (16.12.1999)

PCT

(10) International Publication Number
WO 99/64078 A3

(51) International Patent Classification⁶: A61L 15/00, (81) Designated States (*national*): AE, AL, AM, AT, AT (utility model), AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, CZ (utility model), DE, DE (utility model), DK, DK (utility model), EE, EE (utility model), ES, FI, FI (utility model), GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SK (utility model), SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZA, ZW.

(21) International Application Number: PCT/US99/13073

(22) International Filing Date: 9 June 1999 (09.06.1999)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data: 98110597.6 9 June 1998 (09.06.1998) EP

(71) Applicant (*for all designated States except US*): THE PROCTER & GAMBLE COMPANY [US/US]; One Procter & Gamble Plaza, Cincinnati, OH 45202 (US).

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): CORZANI, Italo [IT/IT]; Via Fontevicchia, 40, I-66100 Chieti (IT). PALUMBO, Gianfranco [IT/DE]; Georgenfeld 7, D-61348 Bad Homburg (DE).

(74) Agents: REED, T., David et al.; The Procter & Gamble Company, 5299 Spring Grove Avenue, Cincinnati, OH 45217-1087 (US).

Published:

— with international search report

(88) Date of publication of the international search report:
20 December 2001

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: SHAPE-FORMED, THREE DIMENSIONAL, MOISTURE VAPOUR PERMEABLE, LIQUID IMPERMEABLE ARTICLES

(57) Abstract: The present invention relates to shape-formed, three dimensional, moisture vapour permeable, liquid impermeable articles comprising moisture vapour permeable, liquid impermeable structures comprising a thermoplastic composition having a higher processability. The thermoplastic compositions comprise preferred thermoplastic polymers and suitable plasticisers to adjust the viscosity of the composition at the process conditions. The shape-formed three dimensional articles of the present invention can

WO 99/64078 A3

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 99/13073

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 A61L15/00 C08K5/00 //C08L101:00

According to International Patent Classification (IPC) or to both national classification and IPC.

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 A61L C08L C08K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 226 439 A (GRACE W R & CO) 24 June 1987 (1987-06-24) claims 1,3,6,11,12 page 6, line 30 - line 35	1-3,6-10
A	EP 0 805 182 A (KUREHA CHEMICAL IND CO LTD) 5 November 1997 (1997-11-05) claims 1,7,9 page 5, line 11 - line 15 page 7, line 50 - line 58 table 1	1
A	EP 0 806 283 A (KUREHA CHEMICAL IND CO LTD) 12 November 1997 (1997-11-12) claims 1,9,11 page 6, line 9 - line 13 page 9, line 43 - line 52 table 1	1
-/-		

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

14 October 1999

Date of mailing of the international search report

25/10/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl.
Fax: (+31-70) 340-3016

Authorized officer

Niaounakis, M

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 99/13073

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	<p>US 5 424 346 A (SINCLAIR RICHARD G) 13 June 1995 (1995-06-13) claims 1,5,15 column 8, line 17 - line 19; figure 5; example 30 column 9, line 58 - line 61</p>	1
A	<p>US 4 123 410 A (LEE JR GIM F) 31 October 1978 (1978-10-31) claims 1,4,9 table 1</p>	1

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 99/13073

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0226439 A	24-06-1987	AT 66685 T	15-09-1991
		AU 603076 B	08-11-1990
		AU 6601286 A	11-06-1987
		BR 8605989 A	15-09-1987
		CA 1288922 A	17-09-1991
		DE 3681135 A	02-10-1991
		GR 3002778 T	25-01-1993
		JP 1956592 C	10-08-1995
		JP 6074340 B	21-09-1994
		JP 62209144 A	14-09-1987
		MX 169228 B	25-06-1993
		US 4826493 A	02-05-1989
		US 4880592 A	14-11-1989
EP 0805182 A	05-11-1997	JP 10072529 A	17-03-1998
EP 0806283 A	12-11-1997	JP 10337772 A	22-12-1998
US 5424346 A	13-06-1995	AU 8660191 A	30-03-1992
		CA 2091185 A	07-03-1992
		EP 0548284 A	30-06-1993
		FI 930992 A	05-03-1993
		JP 6504799 T	02-06-1994
		WO 9204413 A	19-03-1992
		US 5767222 A	16-06-1998
		US 5444113 A	22-08-1995
		US 5556895 A	17-09-1996
		US 5801223 A	01-09-1998
		US 5760118 A	02-06-1998
		US 5834582 A	10-11-1998
		US 5502158 A	26-03-1996
		AT 177134 T	15-03-1999
		DE 68928938 D	08-04-1999
		DE 68928938 T	30-09-1999
		DK 50391 A	20-03-1991
		EP 0428620 A	29-05-1991
		HU 64576 A	28-01-1994
		WO 9001521 A	22-02-1990
		AU 634723 B	04-03-1993
		CA 1339026 A	25-03-1997
		JP 2725870 B	11-03-1998
		JP 4504731 T	20-08-1992
US 4123410 A	31-10-1978	NONE	